



Metalflake® Corporation
7 Arrowhead Circle Rowley, MA 01969
1-508-932-3339 MetalFlake@Comcast.net

APPLICATION GUIDE MICROGLOW Ultra-Thin Polyester Flake




1. Prepare surface:

- A. If surface is stripped bare, sand with oscillating sander using #180 grit paper, Wash thoroughly with a metal conditioner.
- B. If the existing surface is a factory baked finish in good condition, scuff with #400 sand paper and apply a bleed sealer after applying a Primer-Surfacer. Otherwise, we recommend removing finish down to original surface. (A bleeder-sealer should be used over all primers and other existing finishes)

2. Prime with 3 coats of Primer-Surfacer. Allow 15 minutes drying time between first two coats and 45 minutes after final coat. Sand with #360 grit paper.

3. Mix 3-4 ounces of Microglow to a quart of reduced (one-to-one) Clear Acrylic lacquer, and apply 3 or more coats, depending upon the degree of coverage desired, and alternate spraying direction with each coat. Use 2 ball bearings in cup and hand agitate constantly to keep flake in suspension. Microglow can also be used as a super brilliant ground coat for Candy Apple colors. Alternate spray pattern with each coat to avoid streaking.

SPRAY PATTERN:

First coat	Second coat	Third coat
		

Use a Devilbiss #043 #30, or #306 nozzle or their equivalent to apply flake coats (use 25 lbs. pressure at the gun.) Allow 10 minutes drying time between each coat.

Other Suggested Uses:

- Add to any automotive metallic paint for superior brilliance.
- Apply over black base. Then apply a candy color to obtain a deep metallic color.

4. Final Finishing:

Option #1. Apply enough Clear Acrylic to allow for sanding without exposing the Spindrif (14-18 coats suggested.) Allow 10 minutes drying time between coats. After final coat, allow 3 weeks drying time before sanding with #320 grit sand paper using an oscillating sander until all orange peel disappears. All edges and sharp curves must be hand sanded to avoid sanding through to flake. Apply 2 more coats of Clear Acrylic. Allow to dry overnight, then wet-sand with #1000 grit paper, compound with buffing wheel and wax.

Option #2. Apply enough Clear Acrylic to allow for sanding without exposing the flake (14-18 coats suggested) Allow 10 minutes drying time between coats. After final coat allow 3 weeks drying time before sanding with #320 grit sand paper using an oscillating sander until all orange peel disappears. All edges and sharp curves must be hand sanded to avoid sanding through to flake. Apply 3 coats of catalyzed Crysta-Crylor for "Wet Look". 3 coats of catalyzed Polygloss Clear, allowing 1 hour drying time between first two coats and 4 hours between second and third coats. Do not re-coat-can cause wrinkling and/or lifting.